

WHAT IS CLAIMED IS

1. A chip package structure comprising:

an organic substrate;

a die, wherein the die has an active surface, a backside that is opposite to the

5 active surface, and a plurality of metal pads located on the active surface, whereas the

backside of the die is adhered to the organic substrate; and

a thin-film circuit layer located on top of the organic substrate and the die and
has an external circuitry, wherein the external circuitry is electrically connected to the

metal pads of the die and extends to a region outside the active surface of the die, the

10 external circuitry has a plurality of bonding pads located on a surface layer of the thin-

film circuit layer and each bonding pad is electrically connected to the corresponding

metal pad of the die.

2. The structure in claim 1, wherein the die has an internal circuitry and a plurality of

active devices located on the active surface of the die and the internal circuitry is

15 electrically connected to the active devices, whereas the internal circuitry forms the metal

pads.

3. The structure in claim 2, wherein a signal from one of the active devices is

transmitted to the external circuitry via the internal circuitry, and from the external

circuitry back to one of the active devices via the internal circuitry.

4. The structure in claim 3, wherein a width, length, and thickness of traces of the external circuitry are greater than corresponding traces of the internal circuitry.

5. The structure in claim 1, wherein the external circuitry further comprising a power/ground bus.

6. The structure in claim 1, wherein the thin-film circuit layer comprising at least a patterned wiring layer and a dielectric layer, the dielectric layer is located on top of the organic substrate and the die, and the patterned wiring layer is located on top of the dielectric layer, whereas the patterned wiring layer is electrically connected to the metal pads of the die through the dielectric layer and forms the external circuitry and the bonding pads of the external circuitry.

7. The structure in claim 6, wherein the dielectric layer has a plurality of thru-holes, and the patterned wiring layer is electrically connected to the metal pads of the die by the thru-holes.

8. The structure in claim 6, wherein a via is located inside each thru-hole, and the patterned wiring layer is electrically connected to the metal pads of the die by the vias.

9. The structure in claim 6, wherein the patterned wiring layer and the vias form the external circuitry.

10. The structure of the claim 6, wherein the external circuitry further comprising at least one passive device.

11. The structure in claim 6, wherein the passive device is selected from a group consisting of a resistor, an inductor, a capacitor, a wave-guide, a filter, and a micro
5 electronic mechanical sensor (MEMS).

12. The structure in claim 10, wherein the passive device is formed by a part of the patterned wiring layer.

13. The structure in claim 6, wherein a material of the dielectric layer is selected from a group consisting of polyimide, benzocyclobutene, porous dielectric material, and
10 stress buffer material.

14. The structure in claim 1, wherein the thin-film circuit layer comprising a plurality of patterned wiring layers and a plurality of dielectric layers, in which the patterned wiring layers and dielectric layers are alternately formed and the patterned wiring layers are electrically connected to the neighboring patterned wiring layers
15 through the dielectric layer, one of the dielectric layers is formed between the thin-film circuit layer and the organic substrate, the patterned wiring layer that is closest to the organic substrate is electrically connected to the metal pads of the die through the dielectric layer that is closest to the organic substrate, where the patterned wiring layer

that is furthest away from the organic substrate forms the bonding pads.

15. The structure in claim 14, wherein each of the dielectric layers has a plurality of thru-holes, by which each of the patterned wiring layer is electrically connected the neighboring patterned wiring layers, where the patterned wiring layer that is closest to the organic substrate is electrically connected to the metal pads of the die through the dielectric layer.

16. The structure in claim 15, wherein a via is located in each thru-hole, by which the patterned wiring layers are electrically connected to the neighboring patterned wiring layers, where the patterned wiring layer that is closest to the organic substrate is electrically connected to the metal pads of the die by the vias.

17. The structure in claim 16, wherein the patterned wiring layers and the vias form the external circuitry.

18. The structure in claim 14, wherein the external circuitry further comprising a passive device.

19. The structure in claim 18, wherein the passive device is selected from a group consisting of a resistor, an inductor, a capacitor, a wave-guide, a filter, and a micro electronic mechanical sensor (MEMS).

20. The structure in claim 18, wherein the passive device is formed by a part of the

patterned wiring layer.

21. The structure in claim 18, wherein a material of the dielectric layer is selected from a group consisting of polyimide, benzocyclobutene, porous dielectric material, and stress buffer material.

5 22. The structure in claim 1, wherein the organic substrate further comprising an inwardly protruded area located on a surface of the organic substrate, where the backside of the die is adhered to a bottom of the inwardly protruded area.

23. The structure in claim 1, wherein the organic substrate comprising an organic layer and a heat conducting layer formed overlapping, a surface of the organic substrate is
10 a side of the heat conducting layer that is further away from the organic layer, the organic layer has at least one opening that penetrates through the organic layer used to form an inwardly protruded area, and the backside of the die is adhered to a bottom of the inwardly protruded area.

24. The structure in claim 23, wherein the heat conducting layer comprising a metal.

15 25. The structure in claim 1 further comprising a filling layer located between a surface of the organic substrate and the thin-film circuit layer and surrounding the peripheral of the die, and a surface of the filling layer is planar to the active surface of the die.

26. The structure in claim 25, wherein a material of the filling layer is selected from a group consisting of epoxy and polymer.

27. The structure in claim 1 further comprising a passivation layer located on top of the thin-film circuit layer and exposing the bonding pads.

5 28. The structure in claim 1 further comprising a plurality of bonding points located on the bonding pads.

29. The structure in claim 28, wherein the bonding points are selected from a group consisting of solder balls, bumps, and pins.

30. A chip package structure comprising:

10 an organic substrate;

a plurality of dies, wherein each die has an active surface, a backside that is opposite to the active surface, and a plurality of metal pads located on the active surface, whereas the backside of each die is adhered to the organic substrate; and

a thin-film circuit layer located on top of the organic substrate and the die and

15 has an external circuitry, wherein the external circuitry is electrically connected to the metal pads of the die and extends to a region outside the active surface of the die, the external circuitry has a plurality of bonding pads located on a surface layer of the thin-film circuit layer and each bonding pad is electrically connected to a corresponding metal

pad of the die.

31. The structure in claim 30, wherein the dies perform same functions.

32. The structure in claim 30, wherein the dies perform different functions.

33. The structure in claim 30, wherein the dies have an internal circuitry and a

5 plurality of active devices located on the active surface of the die, and the internal
circuitry is electrically connected to the active devices, whereas the internal circuitry
forms the metal pads.

34. The structure in claim 33, wherein a signal from one of the active devices is
transmitted to the external circuitry via the internal circuitry, and from the external
10 circuitry back to one of the active devices via the internal circuitry..

35. The structure in claim 34, wherein a width, length, and thickness of the traces of
the external circuitry are greater than corresponding traces of the internal circuitry.

36. The structure in claim 30, wherein the external circuitry further comprising a
power/ground bus.

15 37. The structure in claim 30, wherein the thin-film circuit layer comprising at least a
patterned wiring layer and a dielectric layer, the dielectric layer is located on top of the
organic substrate and the die, and the patterned wiring layer is located on top of the
dielectric layer, whereas the patterned wiring layer is electrically connected to the metal

pads of the die through the dielectric layer and forms the external circuitry and the bonding pads of the external circuitry.

38. The structure in claim 37, wherein the dielectric layer has a plurality of thru-holes, and the patterned wiring layer is electrically connected to the metal pads of the die by the thru-holes.

39. The structure in claim 38, wherein a via is located inside each thru-hole, and the patterned wiring layer is electrically connected to the metal pads of the die by the vias.

40. The structure in claim 39, wherein the patterned wiring layer and the vias form the external circuitry.

41. The structure of the claim 37, wherein the external circuitry further comprising at least one passive device.

42. The structure in claim 41, wherein the passive device is selected from a group consisting of a resistor, an inductor, a capacitor, a wave-guide, a filter, and a micro electronic mechanical sensor (MEMS).

43. The structure in claim 41, wherein the passive device is formed by a part of the patterned wiring layer.

44. The structure in claim 37, wherein a material of the dielectric layer is selected from a group consisting of polyimide, benzocyclobutene, porous dielectric material, and

stress buffer material.

45. The structure in claim 30, wherein the thin-film circuit layer comprising a plurality of patterned wiring layers and a plurality of dielectric layers, in which the patterned wiring layers and dielectric layers are alternately formed and the patterned wiring layers are electrically connected to the neighboring patterned wiring layers through the dielectric layer, one of the dielectric layers is formed between the thin-film circuit layer and the organic substrate, the patterned wiring layer that is closest to the organic substrate is electrically connected to the metal pads of the dies through the dielectric layer that is closest to the organic substrate, where the patterned wiring layer that is furthest away from the organic substrate forms the bonding pads.

46 The structure in claim 45, wherein each of the dielectric layers has a plurality of thru-holes, by which each of the patterned wiring layer is electrically connected the neighboring patterned wiring layers, where the patterned wiring layer that is closest to the organic substrate is electrically connected to the metal pads of the dies through the dielectric layer.

47. The structure in claim 46, wherein a via is located in each thru-hole, by which the patterned wiring layers are electrically connected to the neighboring patterned wiring layers, where the patterned wiring layer that is closest to the organic substrate is

electrically connected to the metal pads of the die by the vias.

48. The structure in claim 47, wherein the patterned wiring layers and the vias form the external circuitry.

49. The structure in claim 45, wherein the external circuitry further comprising a
5 passive device.

50. The structure in claim 49, wherein the passive device is selected from a group consisting of a resistor, an inductor, a capacitor, a wave-guide, a filter, and a micro electronic mechanical sensor (MEMS).

51. The structure in claim 49, wherein the passive device is formed by a part of the
10 patterned wiring layer.

52. The structure in claim 45, wherein a material of the dielectric layer is selected from a group consisting of polyimide, benzocyclobutene, porous dielectric material, and stress buffer material.

53. The structure in claim 30, wherein the organic substrate further comprising a
15 plurality of inwardly protruded areas located on a surface of the organic substrate and the backside of the dies is adhered to a bottom of the inwardly protruded areas.

54. The structure in claim 30, wherein the organic substrate comprising an organic layer and a heat conducting layer formed thereon together, a top surface of the organic

substrate is a side of the heat conducting layer that is further away from the organic layer, the organic layer has a plurality of openings that penetrate through the organic layer used to form the inwardly protruded areas, and the backside of the dies are adhered to a bottom of the inwardly protruded areas.

5 55. The structure in claim 54, wherein the heat conducting layer comprising a metal.

56. The structure in claim 30 further comprising a filling layer located between a surface of the organic substrate and the thin-film circuit layer and surrounding the peripheral of the die, and a surface of the filling layer is planar to the active surface of the die.

10 57. The structure in claim 56, wherein a material of the filling layer is selected from a group consisting of epoxy and polymer.

58. The structure in claim 30 further comprising a passivation layer located on top of the thin-film circuit layer and exposing the bonding pads.

15 59. The structure in claim 30 further comprising a plurality of bonding points located on the bonding pads.

60. The structure in claim 59, wherein the bonding points are selected from a group consisting of solder balls, bumps, and pins.

61. A chip packaging method comprising:

providing an organic substrate with a surface;

providing a plurality of dies, wherein each die has an active surface, a backside that is opposite to the active surface, and a plurality of metal pads located on the active surface, whereas the backside of each die is adhered to the surface of the organic

5 substrate;

allocating a first dielectric layer on top of the surface of the organic substrate and the active surface of the dies; and

allocating a first patterned wiring layer on top of the first dielectric layer, wherein the first patterned wiring layer is electrically connected to the metal pads of the dies through the first dielectric layer, extends to a region outside of an area above the active surfaces of the dies, and has a plurality of first bonding pads.

62. The method of claim 61, wherein the dies perform same functions.

63. The method of claim 61, wherein the dies perform different functions.

64. The method of claim 61, wherein the organic substrate has a plurality of inwardly protruded areas located on the surface of the organic substrate, where the backside of each die is adhered to a bottom of an inwardly protruded area.

65. The method of claim 64, wherein the organic substrate comprising at least a first insulating core board and a second insulating core board formed overlapping, wherein the

first insulating core board has a plurality of openings used to form inwardly protruded areas with the second insulating core board.

66. The method of claim 64, wherein the openings and the organic substrate are formed together and a method of fabricating the organic substrate comprising injection molding.

67. The method of claim 64, wherein the organic substrate comprising an organic layer and a heat conducting layer formed overlapping, a surface of the organic substrate is a side of the heat conducting layer that is further away from the organic layer, the organic layer has a plurality of openings that penetrates through the organic layer used to form the inwardly protruded areas, and the backside of the dies is adhered to a bottom of the inwardly protruded areas.

68. The method of claim 67, wherein the openings and the organic substrate are formed together and a method of fabricating the organic substrate comprising injection molding.

69. The method of claim 67, wherein the heat conducting layer comprising a metal.

70. The method of claim 61, wherein after adhering the dies and before allocating the first dielectric layer, further comprising allocating a filling layer on top of the surface of the organic substrate and surrounding the peripheral of the dies, and a top surface of the

filling layer is planar to the active surface of the dies.

71. The method of claim 70, wherein a material of the filling layer is selected from a group consisting of epoxy and polymer.

72. The method of claim 61, wherein after allocating the first dielectric layer and before allocating the first patterned wiring layer, further comprising patterning the first dielectric layer to form a plurality of first thru-holes that penetrates through the first dielectric layer, and the first patterned conductive is electrically connected to the metal pads of the dies by the first thru-holes.

73. The method of claim 72, wherein when allocating the first patterned wiring layer on the first dielectric layer, further includes allocating a plurality of first vias by filling part of a conductive material of the first patterned conductive layer into the first thru-holes to electrically connect the first patterned wiring layer and the metal pads of the dies by the first vias.

74. The method of claim 72, wherein when allocating the first patterned wiring layer on top of the first dielectric layer, further comprising filling the first thru-holes with a conductive material to form a plurality of first vias, by which the first patterned wiring layer and the metal pads are electrically connected.

75. The method of claim 61, wherein a material of the first dielectric layer is selected

from a group consisting of polyimide, benzocyclobutene, porous dielectric material, and stress buffer material.

76. The method of claim 61, wherein the method of allocating the first patterned wiring layer on top of the first dielectric layer is selected from a group consisting of

5 sputtering, electroplating, and electro-less plating.

77. The method of claim 61, further comprising allocating a patterned passivation layer on top of the first dielectric layer and the first patterned wiring layer and exposing the first bonding pads.

78. The method of claim 61, further comprising allocating a bonding point on the
10 first bonding pads.

79. The method of claim 78, wherein the bonding points are selected from a group consisting of solder balls, bumps, and pins.

80. The method of claim 78, further comprising singularizing the chip package structure after allocating the bonding point on the bonding pads.

15 81. The method of claim 80, wherein a singularization of the chip package structure is performed on a single die.

82. The method of claim 80, wherein a singularization of the chip package structure is performed on a plurality of dies.

83. The method of claim 61 further comprising:

(a) allocating a second dielectric layer on top of the first dielectric layer and the first patterned wiring layer; and

(b) allocating a second patterned wiring layer on top the second dielectric layer,

5 wherein the second patterned wiring layer is electrically connected to the first patterned wiring layer through the second dielectric layer, and the second patterned wiring layer extends to a region outside the active surface of the die and has a plurality of second bonding pads.

84. The method of claim 83, wherein after allocating the second dielectric layer and before allocating the second patterned wiring layer, further comprising patterning the 10 second dielectric layer to form a plurality of second thru-holes, which corresponds to the first thru-holes and penetrates the second dielectric layer, to electrically connect to the first patterned wiring layer.

85. The method of claim 84, wherein when allocating the second patterned wiring 15 layer on top of the second dielectric layer, further comprising filling the second thru-holes with part of a conductive material of the second patterned wiring layer to form a plurality of second vias, by which the second patterned wiring layer is electrically connected to the first patterned wiring layer.

86. The method of claim 84, wherein before allocating the second patterned wiring layer on top of the second dielectric layer, further comprising filling the second thru-holes with a conductive material to form a plurality of second vias, by which the second patterned wiring layer is electrically connected to the first patterned wiring layer.

5 87. The method of claim 83, wherein a material of the second dielectric layer is selected from a group consisting of polyimide, benzocyclobutene, porous dielectric material, and stress buffer material.

88. The method of claim 83, wherein the method of allocating the second patterned wiring layer on the second dielectric layer is selected from a group consisting of
10 sputtering, electroplating, and electro-less plating.

89. The method of claim 83, further comprising allocating a patterned passivation layer on top of the second dielectric layer and the second patterned wiring layer and exposing the second bonding pads.

90. The method of claim 83, further comprising allocating a bonding point on the
15 second bonding pads.

91. The method of claim 90, wherein the bonding points are selected from a group consisting of solder balls, bumps, and pins.

92. The method of claim 90, further comprising singularizing the chip package

structure after allocating the bonding point on the second bonding pads.

93. The method of claim 92, wherein a singularization of the chip package structure is performed on a single die.

94. The method of claim 92, wherein a singularization of the chip package structure is performed on a plurality of dies.

95. The method of claim 83, further comprising repeating step (a) and step (b) a plurality of times.

96. The method of claim 95 further comprising allocating a patterned passivation layer on the second dielectric layer and the second patterned wiring layer that is furthest away from the organic substrate and exposing the second bonding pads of the second patterned wiring layer that is furthest away from the organic substrate.

97. The method of claim 95, further comprising allocating a bonding point on the second bonding pads of the second dielectric layer that is furthest away from the organic substrate.

98. The method of claim 97, wherein the bonding points are selected from a group consisting of solder balls, bumps, and pins.

99. The method of claim 97, further comprising singularizing the chip package structure after allocating the bonding point on the second bonding pads.

100. The method of claim 99, wherein a singularization of the chip package structure is performed on a single die.

101. The method of claim 100, wherein a singularization of the chip package structure is performed on a plurality of dies.

5 102. A chip packaging method comprising:

providing an insulating substrate with a first surface;

providing a plurality of dies, wherein each die has an active surface and a
backside that is opposite to the active surface and a plurality of metal pads located on the
active surface, whereas the active surface of each die is adhered to the first surface of the
10 insulating substrate;

allocating a filling layer on top of the first surface of the insulating substrate
and surrounding the dies;

planarizing and thinning of the filling layer and the dies;

15 providing an organic substrate with a second surface and adhering the second
surface of the organic substrate to the filling layer and the dies; and

allocating a first patterned wiring layer on top of the insulating substrate,
wherein the first patterned wiring layer is electrically connected to the metal pads of the
dies through the insulating substrate, extends to a region outside the active surfaces of the

dies, and has a plurality of first bonding pads.

103. The method of claim 102, wherein the dies perform same functions.

104. The method of claim 102, wherein the dies perform different functions.

105. The method of claim 102, wherein a material of the insulating substrate is

5 selected from a group consisting of glass, organic, and organic material.

106. The method of claim 102, wherein a material of the filling layer is selected from
a group consisting of epoxy and polymer.

107. The method of claim 102, wherein a thickness of the insulating substrate is in a
range from about 2 microns to 200 microns.

108. The method of claim 102, wherein after adhering the organic substrate and
before patterning the insulating substrate, further comprising thinning a thickness of the
insulating substrate.

109. The method of claim 108, wherein a thickness of the insulating substrate after
thinning is in a range from about 2 microns to 200 microns.

110. The method of claim 102, wherein the method of allocating the first patterned
wiring layer on the insulating substrate is selected from a group consisting of sputtering,
electroplating, and electro-less plating.

111. The method of claim 102, wherein before allocating the first patterned wiring

layer on the insulating substrate, further comprising removing part of the insulating substrate to form a plurality of first thru-holes, the first patterned wiring layer, and a plurality of first vias, which correspond to the metal pads and penetrate the insulating substrate, and the first patterned wiring layer is electrically connected to the metal pads by the first vias.

112. The method of claim 111, wherein when allocating the first patterned wiring layer on the insulating substrate, further comprising filling the first thru-holes with part of a conductive material of the first patterned wiring layer to form a plurality of first vias, by which the first patterned wiring layer is electrically connected to the metal pads of the dies.

113. The method of claim 111, wherein before allocating the first patterned wiring layer on the insulating substrate, further comprising filling a conductive material in the first thru-holes to form a plurality of first vias, by which the first patterned wiring layer is electrically connected to the metal pads of the dies.

114. The method of claim 102 further comprising allocating a patterned passivation layer on the insulating substrate and the first patterned wiring layer and exposing the first bonding pads.

115. The method of claim 109 further comprising allocating a bonding point on the

first bonding pads.

116. The method of claim 115, wherein the bonding points are selected from a group consisting of solder balls, bumps, and pins.

117. The method of claim 115, further comprising singularizing the chip package structure after allocating the bonding point on the bonding pads.

118. The method of claim 117, wherein a singularization of the chip package structure is performed on a single die.

119. The method of claim 117, wherein a singularization of the chip package structure is performed on a plurality of dies.

120. The method of claim 102 further comprising:

(a) allocating a dielectric layer on top of the insulating substrate and the first patterned wiring layer; and

(b) allocating a second patterned wiring layer on top the insulating substrate, wherein the second patterned wiring layer is electrically connected to the first patterned wiring layer through the insulating substrate, and the second patterned wiring layer extends to a region outside of the active surface of the die and has a plurality of second bonding pads.

121. The method of claim 120, wherein after allocating the dielectric layer and

before allocating the second patterned wiring layer, further comprising patterning the dielectric layer to form a plurality of second thru-holes, which corresponds to the first bonding pads and penetrates the dielectric layer, to electrically connect to the first patterned wiring layer to the second patterned wiring layer.

5 122. The method of claim 121, wherein when allocating the second patterned wiring layer on top of the dielectric layer, further comprising filling the second thru-holes with part of a conductive material of the second patterned wiring layer to form a plurality of second vias, by which the second patterned wiring layer is electrically connected to the first patterned wiring layer.

10 123. The method of claim 121, wherein before allocating the second patterned wiring layer on top of the dielectric layer, further comprising filling the second thru-holes with a conductive material to form a plurality of second vias, by which the second patterned wiring layer is electrically connected to the first patterned wiring layer.

15 124. The method of claim 120, wherein a material of the second dielectric layer is selected from a group consisting of polyimide, benzocyclobutene, porous dielectric material, and stress buffer material.

125. The method of claim 120, wherein a method of allocating the second patterned wiring layer on the second dielectric layer is selected from a group consisting of

sputtering, electroplating, and electro-less plating.

126. The method of claim 120, further comprising allocating a patterned passivation layer on top of the second dielectric layer and the second patterned wiring layer and exposing the second bonding pads.

5 127. The method of claim 120, further comprising allocating a bonding point on the second bonding pads.

128. The method of claim 127, wherein the bonding points are selected from a group consisting of solder balls, bumps, and pins.

129. The method of claim 127, further comprising singularizing the chip package
10 structure after allocating the bonding point on the second bonding pads.

130. The method of claim 129, wherein a singularization of the chip package structure is performed on a single die.

131. The method of claim 129, wherein a singularization of the chip package structure is performed on a plurality of dies.

15 132. The method of claim 120, further comprising repeating step (a) and step (b) a plurality of times.

133. The method of claim 132 further comprising allocating a patterned passivation layer on the second dielectric layer and the second patterned wiring layer that is furthest

away from the organic substrate and exposing the second bonding pads of the second patterned wiring layer that is furthest away from the organic substrate.

134. The method of claim 132, further comprising allocating a bonding point on the second bonding pads of the second patterned wiring layer that are furthest away from the organic substrate.

135. The method of claim 134, wherein the bonding points are selected from a group consisting of solder balls, bumps, and pins.

136. The method of claim 134, further comprising singularizing the chip package structure after allocating the bonding point on the second bonding pads.

137. The method of claim 136, wherein a singularization of the chip package structure is performed on a single die.

138. The method of claim 136, wherein a singularization of the chip package structure is performed on a plurality of dies.

139. A chip packaging method comprising:

providing a substrate with a first surface;

providing a plurality of dies, wherein each die has an active surface, a backside that is opposite to the active surface, and a plurality of metal pads located on the active surface, whereas the active surface of each die is adhered to the first surface of the

substrate;

allocating a first filling layer on top of the first surface of the substrate and
surrounding the dies;

planarizing and thinning of the filling layer and the dies;

5 providing an organic substrate with a second surface and adhering the second
surface of the organic substrate to the filling layer and the dies;

removing the first filling layer and the substrate;

allocating a first dielectric layer on the second surface of the organic substrate
and the active surface of the dies; and

10 allocating a first patterned wiring layer on top of the first dielectric layer,
wherein the first patterned wiring layer is electrically connected to the metal pads of the
dies through the first dielectric layer, extends to a region outside the active surfaces of the
dies, and has a plurality of first bonding pads.

140. The method of claim 139, wherein the dies perform same functions.

15 141. The method of claim 139, wherein the dies perform different functions.

142. The method of claim 139, wherein a material of the substrate is selected from a
group consisting of glass, organic, and organic material.

143. The method of claim 139, wherein a material of the first filling layer is selected

from a group consisting of epoxy and polymer.

144. The method of claim 139, wherein after adhering the organic substrate and before removing the first filling layer and the substrate, further comprising allocating a second filling layer on top of the second surface of the organic substrate, the second
5 filling layer surrounds a peripheral of the dies and has a top surface that is planar to the active surface of the dies.

145. The method of claim 144, wherein a material of the second filling layer is selected from a group consisting of epoxy and polymer.

146. The method of claim 139, wherein after allocating the first dielectric layer and
10 before allocating the first patterned wiring layer, further comprising patterning the first dielectric layer to form a plurality of first thru-holes, by which the first patterned wiring layer is electrically connected to the metal pads of the dies.

147. The method of claim 146, wherein when allocating the first patterned wiring layer on top of the first dielectric layer, further comprising filling the first thru-holes with
15 part of a conductive material of the first patterned wiring layer to form a plurality of first vias, by which the first patterned wiring layer is electrically connected to the metal pads of the dies.

148. The method of claim 146, wherein before allocating the first patterned wiring

layer on top of the first dielectric layer, further comprising filling the first thru-holes with a conductive material to form a plurality of first vias, by which the first patterned wiring layer is electrically connected to the metal pads of the dies.

149. The method of claim 139, wherein a material of the first dielectric layer is
5 selected from a group consisting of polyimide, benzocyclobutene, porous dielectric material, and stress buffer material.

150. The method of claim 139, wherein a method of allocating the first patterned wiring layer on the first dielectric layer is selected from a group consisting of sputtering, electroplating, and electro-less plating.

10 151. The method of claim 139, further comprising allocating a patterned passivation layer on top of the first dielectric layer and the first patterned wiring layer and exposing the first bonding pads.

152. The method of claim 139, further comprising allocating a bonding point on the first bonding pads.

15 153. The method of claim 152, wherein the bonding points are selected from a group consisting of solder balls, bumps, and pins.

154. The method of claim 152, further comprising singularizing the chip package structure after allocating the bonding point on the first bonding pads.

155. The method of claim 154, wherein a singularization of the chip package structure is performed on a single die.

156. The method of claim 154, wherein a singularization of the chip package structure is performed on a plurality of dies.

5 157. The method of claim 139 further comprising:

(a) allocating a second dielectric layer on top of the first dielectric layer and the first patterned wiring layer; and

(b) allocating a second patterned wiring layer on top the second dielectric layer, wherein the second patterned wiring layer is electrically connected to the first patterned wiring layer through the second dielectric layer, and the second patterned wiring layer extends to a region outside the active surface of the die and has a plurality of second bonding pads.

158. The method of claim 157, wherein after allocating the second dielectric layer and before allocating the second patterned wiring layer, further comprising patterning the second dielectric layer to form a plurality of second thru-holes, which corresponds to the first bonding pads and penetrates the second dielectric layer, to electrically connect to the first patterned wiring layer.

159. The method of claim 158, wherein when allocating the second patterned wiring

layer on top of the second dielectric layer, further comprising filling the second thru-holes with part of a conductive material of the second patterned wiring layer to form a plurality of second vias, by which the second patterned wiring layer is electrically connected to the first patterned wiring layer.

5 160. The method of claim 158, wherein before allocating the second patterned wiring layer on top of the second dielectric layer, further comprising filling the second thru-holes with a conductive material to form a plurality of second vias, by which the second patterned wiring layer is electrically connected to the first patterned wiring layer.

10 161. The method of claim 157, wherein a material of the second dielectric layer is selected from a group consisting of polyimide, benzocyclobutene, porous dielectric material, and stress buffer material.

162. The method of claim 157, wherein a method of allocating the second patterned wiring layer on the second dielectric layer is selected from a group consisting of sputtering, electroplating, and electro-less plating.

15 163. The method of claim 157, further comprising allocating a patterned passivation layer on top of the second dielectric layer and the second patterned wiring layer and exposing the second bonding pads.

164. The method of claim 157, further comprising allocating a bonding point on the

second bonding pads.

165. The method of claim 164, wherein the bonding points are selected from a group consisting of solder balls, bumps, and pins.

166. The method of claim 164, further comprising singularizing the chip package structure after allocating the bonding point on the second bonding pads.

167. The method of claim 166, wherein a singularization of the chip package structure is performed on a single die.

168. The method of claim 166, wherein a singularization of the chip package structure is performed on a plurality of dies.

169. The method of claim 157, further comprising repeating step (a) and step (b) a plurality of times.

170. The method of claim 169 further comprising allocating a patterned passivation layer on the second dielectric layer and the second patterned wiring layer that are furthest away from the organic substrate and exposing the second bonding pads of the second patterned wiring layer that is furthest away from the organic substrate.

171. The method of claim 169, further comprising allocating a bonding point on the second bonding pads of the second patterned wiring layer that is furthest away from the organic substrate.

172. The method of claim 171, wherein the bonding points are selected from a group consisting of solder balls, bumps, and pins.

173. The method of claim 171, further comprising singularizing the chip package structure after allocating the bonding point on the second bonding pads.

5 174. The method of claim 173, wherein a singularization of the chip package structure is performed on a single die.

175. The method of claim 173, wherein a singularization of the chip package structure is performed on a plurality of dies.

176. A chip package structure comprising:

10 an organic substrate;

 a die module comprising an active surface, a backside that is opposite to the active surface, and a plurality of metal pads located on the active surface, whereas the backside of the die module is adhered to the organic substrate;

 a filling layer located on top of the organic substrate and surrounding a
15 peripheral of the die module, a top surface of the filling layer is planar to the active surface of the die module;

 a thin organic layer located on top of the filling layer and the die module; and

 a thin-film circuit layer located on top of the thin organic layer and the die

module and has an external circuitry, wherein the external circuitry is electrically connected to the metal pads of the die module and extends to a region outside the active surface of the die module, the external circuitry has a plurality of bonding pads located on a surface layer of the thin-film circuit layer and each bonding pad is electrically

5 connected to a corresponding metal pad of the die module.

177. The structure in claim 176, wherein the die module comprising a single die.

178. The structure in claim 176, wherein the die module comprising a plurality of dies.

179. The structure in claim 178, wherein the dies perform different functions.

10 180. The structure in claim 176, wherein a material of the filling layer is selected from a group consisting epoxy and polymer.

181. The structure in claim 176, wherein a thickness of the thin organic layer is in a range from about 2 microns to 200 microns.

182. The structure in claim 176, wherein the die module has an internal circuitry and

15 a plurality of active devices located on the active surface of the die module and the internal circuitry is electrically connected to the active devices, whereas the internal circuitry forms the metal pads.

183. The structure in claim 182, wherein a signal from one of the active devices is

transmitted to the external circuitry via the internal circuitry, and from the external circuitry back to one of the active devices via the internal circuitry.

184. The structure in claim 183, wherein a width, length, and thickness of traces of the external circuitry are greater than corresponding traces of the internal circuitry.

5 185. The structure in claim 176, wherein the external circuitry further comprising a power/ground bus.

186. The structure in claim 176, wherein the thin-film circuit layer comprising at least a patterned wiring layer, which is located on the thin organic layer, whereas the patterned wiring layer is electrically connected to the metal pads of the die module
10 through the thin organic layer and forms the external circuitry and the bonding pads of the external circuitry.

187. The structure in claim 186, wherein the thin organic layer has a plurality of thru-holes, and the patterned wiring layer is electrically connected to the metal pads of the die module by the thru-holes.

15 188. The structure in claim 187 wherein a via is located inside each thru-hole, and the patterned wiring layer is electrically connected to the metal pads of the die module by the vias.

189. The structure in claim 188, wherein the patterned wiring layer and the vias form

the external circuitry.

190. The structure of the claim 186, wherein the external circuitry further comprising at least one passive device.

191. The structure in claim 190, wherein the passive device is selected from a group consisting of a resistor, an inductor, a capacitor, a wave-guide, a filter, and a micro electronic mechanical sensor (MEMS).

192. The structure in claim 190, wherein the passive device is formed by a part of the patterned wiring layer.

193. The structure in claim 176, wherein the thin-film circuit layer comprising a plurality of patterned wiring layers and a plurality of dielectric layers, in which the patterned wiring layers and dielectric layers are alternately formed and the patterned wiring layers are electrically connected to the neighboring patterned wiring layers through the dielectric layer, one of the dielectric layers is formed between the thin-film circuit layer and the organic substrate, the patterned wiring layer that is closest to the organic substrate is electrically connected to the metal pads of the die module through the dielectric layer that is closest to the organic substrate, where the patterned wiring layer that is furthest away from the organic substrate forms the bonding pads.

194. The structure in claim 193, wherein the thin organic layer has a plurality of first

thru-holes, by which the patterned wiring layer that is closest to the organic substrate is electrically connected to the metal pads of the die module, and each dielectric layer has a plurality of second thru-holes, by which the patterned wiring layers are electrically connected to the neighboring patterned wiring layers.

5 195. The structure in claim 194, wherein a first via is located inside each first thru-hole and a second via is located inside each second thru-hole, and each patterned wiring layer is electrically connected to the neighboring patterned wiring layers by the second vias, wherein the patterned wiring layer that is closest to the organic substrate is electrically connected to the metal pads of the die module by the first vias.

10 196. The structure in claim 195, wherein the patterned wiring layers, the first vias, and the second vias form the external circuitry.

197. The structure in claim 193, wherein the external circuitry further comprising a passive device.

15 198. The structure in claim 197 wherein the passive device is selected from a group consisting of a resistor, an inductor, a capacitor, a wave-guide, a filter, and a micro electronic mechanical sensor (MEMS).

199. The structure in claim 193, wherein the passive device is formed by a part of the patterned wiring layer.

200. The structure in claim 193, wherein a material of the dielectric layer is selected from a group consisting of polyimide, benzocyclobutene, porous dielectric material, and stress buffer material.

201. The structure in claim 176 further comprising a patterned passivation layer
5 located on top of the thin-film circuit layer and exposing the bonding pads.

202. The structure in claim 176 further comprising a plurality of bonding points
located on the bonding pads.

203. The structure in claim 202, wherein the bonding points are selected from a
group consisting of solder balls, bumps, and pins.

11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2193
2194
2195
2196
219